



Cerium Oxide Powder **COPII**

Grit Size: D10>0,6µm / D50:1,5µ-1,6µm / D90<6,0µm

PRODUCT	Physical Index						
	TREO	CeO2/REO	F	PH	D50	D90	Suspension
COPII	>85	63-67%	4-4,5	7-8	1,4-1,5µm	6,0µm	3ml

COLOR	Chemical Index (%)						
	REO	La2O3/REO	CeO2/REO	Pr6O11/REO	Nd2O3/REO	Fe2O3	
PINK	>85	33-37	63-67	3-4	<0,002	<0,002	
WHITE	>95	33-37	63-67	<0,002	<0,002	<0,002	

Cerium Oxide Powder **COPV**

Grit Size: D10>0,6µm / D50:1,5µ / D90<5,0µm

PRODUCT	Physical Index						
	TREO	CeO2/REO	F	PH	D50	D90	Suspension
COPV	>95	63-67%	4-4,5	7-8	1,5µm	5,0µm	3ml

COLOR	Chemical Index (%)						
	REO	La2O3/REO	CeO2/REO	Pr6O11/REO	Nd2O3/REO	Fe2O3	
PINK	>95	33-37	63-67	3-4	<0,002	<0,002	
WHITE	>95	33-37	63-67	<0,002	<0,002	<0,002	